

Wax Comparison Sheet

*Top Seller in
Brand

Recommended for:

	Make-up	Melt Point	Adhesion	Form	Pour Temp	F/ L	Tarts	Massage
Golden Brands								
GB-415 Container Wax	100% Soy	120°-125°		Flake	90°-100°	8%-10%		
GB-444 Container Wax	Soy & Soy based additives	120°-125°		Flake	125°-145°	9%-11%		
GB-464 Container Wax	Soy & Soy based additives	115°-120°	Adhesion	Flake	125°-145°	7%-9%		
GB- Wax Tart & Melt Wax	Soy & Bio based additives	120°-125°	Great Mold Release	Flake	Heat to 170° Pour above 150°	5%-10%	X	
GB-454	Soy & Coconut	115°-125°	Adhesion	Flake	155°-125°	5%-10%		
NatureWax								
NW-C1 Container Wax	100% Soy/Palm	124°-130°	Complete Pull-Away	Flake	110°-135°	7-10%	X	X
NW-C3 Container Wax *	100% Soy-based	124°-130°	Complete Adhesion	Flake	120°-165°	7-10%	X	X
NW-C6 Container Blend	Soy/Coconut blend (mostly soy)	124°-130°	Complete adhesion	Slab	120°-165°	7-10%	X	X
NW-Elite 200 Container Wax	Soy/ Palm blend (mostly Soy)	125°-135°	Complete Pull-Away	Slab	140°-185°	9-12%	X	
NW-Elite 300 Pillar Wax	100 % Palm with Additives	130°-140°	Self-releasing	Slab	155°-185° (Smooth) 140°-150°	5%	X	
NW-S113 (Base/Blending) Container Wax	100% Soy	111°-116°	Aids in Adhesion	Flake	105°-120°	Up to 10%	X	

NW-C-NUT1 (Additive/ Softener)	100% Hydrogenated Coconut Oil	90°-102°	Improves adhesion of blend it is added to: 1 to 5% for C- 3 or C-1. 10-15% for Elite 200	Solid Cube	Use PT of wax it is added to	Use FL of Base Wax	only recom mende d 1%- 5%	5 to 10% for blends
NW-C-NUT2 (Additive/Softe ner)	98% hydrogenated coconout oil & 2% Hydrogentated Soy	108°-112°	Improves adhesion of blend it is added to: 1 to 5% for C- 3 or C-1. 10-15% for Elite 200	Solid Cube	Use PT of wax it is added to	Use FL of Base Wax	only recom mende d 1%- 5%	5 to 10% for blends

Ecosoya
properties are
on Wax
Properties
Spreadsheet 5.0
under

F:\Fillmore\FCI Inventory\FCI Candle Inventory\Wax Inventory Information\Wax Properties Spreadsheet